Data sheet tests Page 1 of 1



Palziv Ein Hanatziv M.P. Emek Beit Shean 10805 Israel | Tel: +972 46 06 29 99 Fax: +972 46 06 29 58

www.palziv.com contact@palziv.com





Company Number: 570040535 Consol. Busn Number: 557634052

Product Specification - PA250

Last update: 06/25/10

Desc.	Standard	Value	Unit
Density	ISO 845	250	Kg/m³
Tensile strength	ISO 1798	2606	kPa
Elongation	ISO 1798	191	%
Compression 10%	ISO 844	739	kPa
Compression 25%	ISO 844	842	kPa
Compression 50%	ISO 844	1242	kPa
Working Temperature Range	Internal	-60 \ 90	°C
Water Absorption %Vol (max)	Internal	1	%
Shore-A	ASTM D2240	59	А
Shore-OO	ASTM D2240	92	00

Palfoam is a closed cell cross-linked polyethylene foam block.

Tolerances other than the above may be negotiated.

Dimensional stability 24 hr at 70C < 2%.

If holes were created during the foaming process, no more than 6 holes of diameter 2mm per 1m2 sheet are acceptable.

This information on Palfoam chemically cross-linked polyethylene foam is presented to the best of our knowledge. Data represents typical values measured on a 10 mm thick specimen and should be considered as guidelines only. PALZIV Kibbutz Ein Hanatziv 10805 Israel. Tel: 972-4-6062999 Fax: 972-4-6062958

www.palziv.com Email: contact@palziv.com