

Product Specification - PA80

Last update: 10/07/09

Desc.	Standard	Value	Unit
Density	ISO 845	80	Kg/m³
Tensile strength	ISO 1798	957	kPa
Elongation	ISO 1798	172	%
Compression 10%	ISO 844	124	kPa
Compression 25%	ISO 844	155	kPa
Compression 50%	ISO 844	245	kPa
Shore-A	ASTM D2240	25	A
Shore-00	ASTM D2240	70	00

Palfoam is a closed cell cross-linked polyethylene foam block.

Tolerances other than the above may be negotiated.

Dimensional stability 24 hr at 70C < 2%.

If holes were created during the foaming process, no more than 5 holes of diameter 2mm per 1m2 sheet are acceptable.

This information on Palfoam chemically cross-linked polyethylene foam is presented to the best of our knowledge. Data represents typical values measured on a 10 mm thick specimen and should be considered as guidelines only. PALZIV Kibbutz Ein Hanatziv 10805 Israel. Tel: 972-4-6062999 Fax: 972-4-6062958

www.palziv.com Email: contact@palziv.com